


# Franklinite



©2001-2005 Mineral Data Publishing, version 1

**Crystal Data:** Cubic. *Point Group:*  $4/m\bar{3}2/m$ . Typically as octahedra, commonly with rounded edges, to 22 cm; may be modified by {011}, {001}, rare {013}, {051}, others. Also exsolved within other minerals; coarse to fine granular, massive. *Twinning:* On {111} as both twin and composition plane, the spinel law, common.

**Physical Properties:** *Cleavage:* Parting on {111}, fair. *Fracture:* Uneven to subconchoidal. *Tenacity:* Brittle. Hardness =  $\sim 6$  VHN = 852–882 (100 g load). D(meas.) = 5.05–5.22 D(calc.) = 5.163 Strongly to weakly magnetic.

**Optical Properties:** Opaque, translucent in fine fragments. *Color:* Iron-black, brown, red, may be tarnished; in reflected light, white to gray, with dark red internal reflections. *Streak:* Reddish brown to black. *Luster:* Metallic to semimetallic; may be dull.

*Optical Class:* Isotropic.  $n = 2.36(2)$  (Li).

R: (400) 19.2, (420) 19.2, (440) 19.2, (460) 19.2, (480) 19.2, (500) 19.1, (520) 19.0, (540) 18.6, (560) 18.2, (580) 17.8, (600) 17.4, (620) 17.1, (640) 16.8, (660) 16.6, (680) 16.4, (700) 16.3

**Cell Data:** *Space Group:*  $Fd\bar{3}m$ .  $a = 8.43\text{--}8.474$   $Z = 8$

**X-ray Powder Pattern:** Franklin, New Jersey, USA.

2.55 (100), 1.499 (80), 2.99 (70), 1.632 (70), 1.104 (50), 0.978 (50), 2.12 (40)

Chemistry:	(1)	(2)	(3)	(1)	(2)	(3)	
SiO <sub>2</sub>	0.72			MnO	9.96	6.6	0.6
TiO <sub>2</sub>			0.7	ZnO	20.77	26.2	30.25
Al <sub>2</sub> O <sub>3</sub>		0.3	1.25	MgO	0.34	0.3	
Fe <sub>2</sub> O <sub>3</sub>	66.58	66.7	63.9	CaO	0.43		
FeO			3.6	H <sub>2</sub> O	0.71		
				Total	99.51	100.1	100.3

(1) New Jersey, USA; total Fe as Fe<sup>3+</sup>. (2) Do.; by electron microprobe, average of five analyses, total Fe as Fe<sub>2</sub>O<sub>3</sub>. (3) Långban, Sweden; by electron microprobe, average of four analyses, Fe<sup>2+</sup>:Fe<sup>3+</sup> calculated from stoichiometry; corresponds to  $(\text{Zn}_{0.88}\text{Fe}_{0.12})_{\Sigma=1.00}(\text{Fe}_{1.90}\text{Al}_{0.06}\text{Mn}_{0.02}^{2+}\text{Ti}_{0.02})_{\Sigma=2.00}\text{O}_4$ .

**Mineral Group:** Spinel group.

**Occurrence:** In beds and veins formed by high-temperature metamorphism of Fe, Zn, Mn-rich marine carbonate sediments. As a minor mineral in some manganese and iron deposits.

**Association:** Zincite, willemite, calcite, andradite, manganosite, rhodochrosite, gahnite, magnetite, rhodonite, hausmannite, hetaerolite, jacobsonite, braunite, sarkinite, berzeliite, hematite.

**Distribution:** From Franklin and at Sterling Hill, Ogdensburg, Sussex Co., New Jersey, USA. Found at Långban, Värmland, Sweden. Occurs at Hraníčná, Czech Republic. In Kazakhstan, from Nayzatas, Dzhumart, and in the Ushkatyn deposits, Atasui area. At the Pereval marble quarry, near Slyudyanka, Sayan Mountains, south of Lake Baikal, Siberia, Russia. From the Koduru manganese mine, Srikakulam district, Andhra Pradesh, India. At the Bonnie prospect, near Mukinbudin, Western Australia.

**Name:** Named for Franklin Furnace (now Franklin), New Jersey, USA; and in honor of the American statesman, philosopher and inventor Benjamin Franklin (1706–1790).

**References:** (1) Palache, C., H. Berman, and C. Frondel (1944) Dana's system of mineralogy, (7th edition), v. I, 698–707. (2) Berry, L.G. and R.M. Thompson (1962) X-ray powder data for the ore minerals. Geol. Soc. Amer. Mem. 85, 193. (3) Burke, E.A.J. and C. Kieft (1972) Franklinite from Långban, Sweden: a new occurrence. Lithos, 5, 69–72. (4) Shirakashi, T. and T. Kubo (1979) Cation distribution in franklinite by nuclear magnetic resonance. Amer. Mineral., 64, 599–603. (5) O'Neill, H.St.C. (1992) Temperature dependence of the cation distribution in zinc ferrite (ZnFe<sub>2</sub>O<sub>4</sub>) from powder XRD structural refinements. Eur. J. Mineral., 4, 571–580. (6) Dunn, P.J. (1995) Franklin and Sterling Hill, New Jersey. No publisher, n.p., 566–578.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise without the prior written permission of Mineral Data Publishing.